

## SCO Silicone Grease Compound

SCO is a high quality, multi-purpose electrical insulating compound with excellent water and moisture repellence. SCO also has good adhesion and spreading characteristics on dry surfaces of metal, ceramic, rubber, PVC and all forms of electrical insulation, it is also resistant to hardening with age.

- Excellent resistance to water erosion and corrosion from rain, condensation and moisture
- Excellent electrical insulating compound; high resistance to tracking and corona discharge
- Chemically inert, odourless and non-toxic; safe in use
- Consistency similar to petroleum jelly; ideal for sealing applications

<b>Approvals</b>	<b>RoHS-2 Compliant (2011/65/EU):</b> <b>US Military Specification MIL-I-8660B:</b> <b>DEF STAN 68-69:</b>	<b>Yes</b> <b>Meets</b> <b>Meets</b>
------------------	--	--

### Typical Properties

Colour	Colourless
Density, bulk (g/ml)	1.0
Density, aerosol (g/ml)	0.7
Temperature Range (°C)	-50 - 220
Evaporation Weight Loss (% 7 days @ 100°C)	0.2
Evaporation Weight Loss (% 7 days @ 125°C)	0.2
Evaporation Weight Loss (% 30 hours @ 205°C)	<2.5
Cone Penetration Worked (ASTM D217, 60 strokes @ 20°C)	460
Cone Penetration Un-Worked (ASTM D 217 @ 20°C)	230
Cone Penetration Un-Worked (ASTM D 217 @ -40°C)	230
Consistency (NLGI)	0
Oil Bleed / Separation (IP121)	3%
UV Trace	No
Thermal Conductivity (W/m.K)	0.16
Solubility (Weight Loss) in:	
Distilled Water	0.2
Isopropyl Alcohol	8.0
Ethyl Alcohol	3.0
Ethylene Glycol	0.2
Glycerine	0.3

#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR  
T +44 (0)1530 419 600  
F +44 (0)1530 416 640  
BS EN ISO 9001:2008  
Certificate No. FM 32082

**Electrical Properties**

Dielectric Constant (1 MHz)	2.83
Dielectric Constant (1 KHz)	2.80
Dielectric Strength (kV, 1 min)	20
Volume Resistivity (ohm-cm)	1.7 x 10 <sup>15</sup>
Loss Tangent (Tan delta 1MHz)	0.00050
Loss Tangent (Tan delta 1KHz)	0.00013

**Base Oil Properties**

Flash Point, bulk (COC ASTM D 92 (°C))	320
Flash Point, aerosol (COC ASTM D 92 (°C))	-48

**Mechanical Properties**

4 Ball Wear (mm)	2.832
Weld Load (kgf)	126

**Description****Packing****Order Code****Shelf Life**

Silicone Grease Compound	200ml Aerosol	SCO200D	36 Months
	35 ml Luer Lock Syringe	SCO35SL	48 Months
	1 Kg Bulk	SCO01K	48 Months

**Typical Product Applications**

All electrical systems where there is a requirement to prevent ingress of moisture and to protect against corona discharge and airborne contamination. It is particularly useful on high voltage electrical connections, ignition systems and electronic equipment to eliminate electrical tracking. SCO may also be used as a release agent in moulding and casting operations, as a glass stop-cock lubricant or as a cable lubricant prior to the cable being drawn through conduits, harnesses etc.

Revision 1: Oct 2013

**Copyright Electrolube 2013**

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR  
T +44 (0)1530 419 600  
F +44 (0)1530 416 640  
BS EN ISO 9001:2008  
Certificate No. FM 32082